



PROJECT ASSURE DIAMOND VERIFICATION INSTRUMENT STANDARD TEST RESULTS

Assessment Report for: De Beers Group Ignite / SYNTHdetect



Prepared For: Luc Auer Natural Diamond Council Belgium VOF Hoveniersstraat 22 2018 Antwerpen

Received Date: March 22nd 2022 Assessment Dates: June 23rd through July 8th, 2022 Testing ID Number: 2022-03 Report Date: October 3rd 2022 . Approved by:

Quinten Van Avondt Lab Manager

Non Armal

ID:

DIAMOND VERIFICATION INSTRUMENT

Manufacturer's Name:	De Beers Group Ignite
Instrument Model:	SYNTHdetect
Serial Number:	135
Software Version:	1.4.249.1
Lab Manager:	Quinten Van Avondt
Testing Manager:	Cindy De Plukker

Manufacturer stated diamond verification instrument description and features:

- Manual stone feed
- Requires level of operator interpretation (training is required) .
- Multiple stones at once •
- Software available to aid interpretation
- Results: Natural or Refer

Manufacturer stated diamond verification instrument limitations:

- Loose stones and mounted stones (uncovered and not under watch glasses) •
- All shapes
- No stone size limit
- Colorless to near colorless stones (fancy colored will show increased referral rate) •

INSTRUMENT PERFORMANCE ASSESSMENT

ASSESSMENT CRITERIA

The ASSURE testing methodology and performance metrics are dependent on the operational capabilities of the diamond verification instrument being tested. These are defined by the following three categories:

Category 1- Screen diamonds from synthetic diamonds. This category of device is intended for discrimination of diamonds from synthetic diamonds. It cannot distinguish diamonds from diamond simulants and therefore requires stones to be pre-screened to ensure no simulants are introduced into the device.

Category 2 – Screen diamonds from synthetic diamonds and diamond simulants. This category of device is intended for discrimination of diamonds from synthetic diamonds and diamond simulants. This device cannot distinguish synthetic diamonds from diamond simulants.

Category 3 – Screen diamond from synthetic diamonds from diamond simulants. This category of device is intended for discrimination of diamonds, synthetic diamonds and diamond simulants from each other. This device can distinguish synthetic diamonds from diamond simulants.

Instrument performance for classifying the different kinds of stones was assessed against:

	Universiteit	De Beers Group Ignite SYNTHdetect			
	Antwerpen			Testing ID:	2022-03

- Diamond Verification Instrument Standard Part 1 Diamond Verification Instrument for Screening Diamonds from Synthetic Diamonds (09 11 2021)
- Diamond Verification Instrument Standard Part 2 Diamond Verification Instrument for Screening Diamonds from Synthetic Diamonds and Diamond Simulants (09 11 2021)
- Diamond Verification Instrument Standard Part 3 Diamond Verification Instrument for Screening Diamonds, Synthetic Diamonds, and Diamond Simulants (09 11 2021)

as referenced in sections 7.3 and 7.4 of the Diamond Verification Instrument Standard – General Requirements for Evaluation Diamond Verification Instruments (09 11 2021). Any deviations from the Standard are noted below:

None

DEFINITIONS:

Diamond Accuracy	Diamond test stones correctly classified as Diamond.
Synthetic Diamond Accuracy	Synthetic Diamond test stones correctly classified as non-diamond (Synthetic Diamond /Diamond simulant).
Diamond Simulant Accuracy	Diamond Simulant test stones correctly classified as non-diamond (Synthetic Diamond/Diamond Simulant).
Diamond Referral Rate	Diamond test stones classified as Referral.
Synthetic Diamond Referral Rate	Synthetic Diamond test stones classified as Referral.
Simulant Referral Rate	Diamond Simulant test stones classified as Referral.
Diamond False Positive Rate	Non-diamond test stones (Synthetic Diamond / Diamond Simulant) incorrectly classified as Diamond.
Synthetic Diamond False Negative Rate	Synthetic Diamonds incorrectly classified as Diamond.
Diamond Simulant False Negative Rate	Diamond Simulants incorrectly classified as Diamond.
Testing Speed	The average speed at which the diamond verification instrument evaluates the stones in the PRIMARY loose sample set, including set-up time (if any).
Operating Speed	For auto-loading diamond verification instruments only, the average speed at which stones are evaluated once the instrument achieves a steady-state. It does not include set-up time.

LETTERS & REPORTS: Universiteit Antwerpen (UAntwerp) letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the UAntwerp name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of UAntwerp with respect to services rendered shall be limited to the amount of consideration paid for such service and not include any consequential damages. This report or certificate does not relieve sellers/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice clients' right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during our random inspection or testing. UAntwerp has not performed a complete analysis of the product. The results contained in this report indicate that the product has passed or failed the specific tests only. These test results, even if rated as "Passed," do not indicate or certify that the product is safe for commercial or consumer use.

	Universiteit	De Beers Group Ignite SYNTHdetect			
6	Antwerpen			Testing ID:	2022-03

TEST STONE SETS USED FOR EVALUATION

Loose, Polished Stone Test Sets	Diamond	Synthetic Diamond	Diamond Simulant
Primary Sample Set (>2.0 mm, D-J color)	\boxtimes	\boxtimes	\boxtimes
Supplementary Smalls Sample Set (1.0-2.0 mm, D-J color)	\boxtimes	\boxtimes	\boxtimes
Mounted, Polished Stone Test Sets	Diamond	Synthetic Diamond	Diamond Simulant
Primary Sample Set (>2.0 mm, D-J color)	\boxtimes	\boxtimes	\boxtimes
Supplementary Smalls Sample Set (1.0-2.0 mm, D-J color)	\boxtimes	\boxtimes	

Notes: none

CLEANING PROCEDURE OF STONES PRIOR TO TESTING

Test stones sets are cleaned in an ultrasonic bath of isopropanol for 2 minutes and dried prior to testing to reduce grease and electrostatic charge, as per Section 8 of ASSURE Standard.

LABORATORY CONDITIONS AT TIME OF ASSESSMENT

Condition	Requirement	Actual
Temperature (°C)	18 to 25°C	23°C
Humidity (%)	50 to 65%	54%

RESULTS OF INSTRUMENT PERFORMANCE ASSESSMENT – LOOSE STONES

Performance Metric	Primary	Uncertainty ^[1]	Smalls	Uncertainty ^[1]
Diamond accuracy (%)	98.2	0.9	97.9	1.0
Synthetic diamond accuracy (%)	N/A ^[2]	0.0	N/A ^[2]	0.0
Diamond simulant accuracy (%)	N/A ^[3]	0.0	N/A ^[3]	0.0
Diamond referral rate (%)	1.8	0.9	2.1	1.0
Synthetic diamond referral rate (%)	100.0 ^[2]	0.0	100.0 ^[2]	0.0
Diamond simulant referral rate (%)	100.0 ^[3]	0.0	100.0 ^[3]	0.0
Diamond false positive rate (%)	0.0	0.0	0.0	0.0
Synthetic diamond false negative rate (%)	0.0	0.0	0.0	0.0
Diamond simulant false negative rate (%)	0.0	0.0	0.0	0.0

Notes: ^[1] Uncertainty is expressed as absolute +/- range and reflects the consistency of the instrument's classification of stones for each of the three trials performed with the ASSURE sample.

- ^[2] All Synthetic Diamonds reported as referral for this instrument
- ^[3] All Diamond Simulants reported as referral for this instrument

	Universiteit	De Beers Group Ignite SYNTHdetect			
6	Antwerpen			Testing ID:	2022-03

RESULTS OF INSTRUMENT PERFORMANCE ASSESSMENT – MOUNTED STONES

Performance metric	Primary	Small
Diamond accuracy (%)	99.6	100.0
Synthetic diamond accuracy (%)	N/A ^[1]	N/A ^[1]
Diamond simulant accuracy (%)	N/A ^[2]	N/A ^[3]
Diamond referral rate (%)	0.4	0.0
Synthetic diamond referral rate (%)	100.0 ^[1]	100.0 ^[1]
Diamond simulant referral rate (%)	100.0 ^[2]	N/A ^[3]
Diamond false positive rate (%)	0.0	0.0
Synthetic diamond false negative rate (%)	0.0	0.0
Diamond simulant false negative rate (%)	0.0	N/A ^[3]

Notes: ^[1] All Synthetic Diamonds reported as referral for this instrument

- ^[2] All Diamond Simulants reported as referral for this instrument
- ^[3] No Diamond Simulants present in the SMALLS set


INSTRUMENT TESTING SPEED ASSESSMENT

Testing Speed approximates the usage turnaround time that could be expected by a novice user of the diamond verification instrument and is determined by the time required to evaluate the performance of the diamond verification instrument on the Primary Loose stone test set:

- Testing Speed accounts for the time directly associated with stone assessment including loading stones, programming any applicable instrument measurement parameters, analyzing the stones, and segregating the analyzed stones into respective instrument classified groups.
- Testing Speed does not include the time to initially warm-up the diamond verification instrument (if applicable) nor the time to separate diamonds from synthetic diamonds for each of the instrument classified groups of analyzed stones.
- Testing Speed does not include time associated with interruptions to the testing process.

Diamond verification instruments that continuously load and analyze stones (i.e., autoloading diamond verification instruments) shall also be assessed for a steady-state Instrument Operating Speed.

Testing speed, and instrument operating speed if applicable, are measured in triplicate. The mean value is reported in the Speed Test Results table below. The Uncertainty reflects the absolute +/- range of the results measured over the three trials.



SPEED TEST RESULTS (PRIMARY LOOSE SAMPLE)

Category	Stones per hour	Uncertainty
Testing Speed (all devices)	170	15
Operating Speed (auto-loading devices)	n/a ^[1]	n/a ^[1]

Notes: ^[1] not applicable for this device, the device has manual feed

ADDITIONAL FINDINGS

None