

**PROJECT ASSURE
DIAMOND VERIFICATION INSTRUMENT STANDARD
TEST RESULTS**

Assessment Report for: ASDI-500



Prepared For: Luc Auer
Natural Diamond Council Belgium VOF
Hoveniersstraat 22
2018 Antwerpen

Received Date: 17 November 2025
Assessment Dates: 17-19 November 2025
Report Date: 12 January 2026

Approved by:

Didier Backaert
Lab Manager

LETTERS & REPORTS: Bonas reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the Bonas name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of Bonas with respect to services rendered shall be limited to the amount of consideration paid for such service and not include any consequential damages. This report or certificate does not relieve sellers/suppliers from their contractual responsibility regarding the quality/quantity of this delivery, nor does it prejudice clients' right to claim towards sellers/suppliers for compensation for any apparent and/or hidden defects not detected during our random inspection or testing. Bonas has not performed a complete analysis of the product. The results contained in this report indicate that the product has passed or failed the specific tests only. These test results, even if rated as "Passed," do not indicate or certify that the product is safe for commercial or consumer use.



DIAMOND VERIFICATION INSTRUMENT

Manufacturer's Name: Unimec SA / SSEF
Instrument Model: ASDI-500
Serial Number: 6502000
Software Version: PLCv1.23
Lab Manager: Didier Backaert
Analyst/Operator : Nathan De Decker

Manufacturer stated diamond verification instrument description and features:

- Automatic stone feed
- Automatic stone classification
- Automatic stone sorting

Manufacturer stated diamond verification instrument limitations:

- Loose stones
- Round brilliant stone shape
- Stone size from 0.50 mm to 3.80 mm
- D-J colour
- Difference in stone diameter within a test parcel may not exceed +/- 0.05mm

INSTRUMENT PERFORMANCE ASSESSMENT

ASSESSMENT CRITERIA

The ASSURE testing methodology and performance metrics are dependent on the operational capabilities of the diamond verification instrument being tested. These are defined by the following three categories:

Category 1- Screen diamonds from synthetic diamonds. This category of device is intended for discrimination of diamonds from synthetic diamonds. It cannot distinguish diamonds from diamond simulants and therefore requires stones to be pre-screened to ensure no simulants are introduced into the device.

Category 2 – Screen diamonds from synthetic diamonds and diamond simulants. This category of device is intended for discrimination of diamonds from synthetic diamonds and diamond simulants. This device cannot distinguish synthetic diamonds from diamond simulants.

Category 3 – Screen diamond from synthetic diamonds from diamond simulants. This category of device is intended for discrimination of diamonds, synthetic diamonds and diamond simulants from each other. This device can distinguish synthetic diamonds from diamond simulants.



Date: 12 January 2026

Testing ID: 2026-01

Instrument performance for classifying the different kinds of stones was assessed against:

- Diamond Verification Instrument Standard Part 1 – Diamond Verification Instrument for Screening Diamonds from Synthetic Diamonds (18 03 2024)
- Diamond Verification Instrument Standard Part 2 – Diamond Verification Instrument for Screening Diamonds from Synthetic Diamonds and Diamond Simulants (18 03 2024)
- Diamond Verification Instrument Standard Part 3 – Diamond Verification Instrument for Screening Diamonds, Synthetic Diamonds, and Diamond Simulants (18 03 2024)

as referenced in sections 7.3 and 7.4 of the Diamond Verification Instrument Standard – General Requirements for Evaluation Diamond Verification Instruments (18 03 2024). Any deviations from the Standard are noted below:

Notes: The ASDI-500 has an upper size limit of 3.8 mm. Stones with greater diameter than 3.8 mm (30 out of 500) were removed from the PRIMARY sample set prior to conducting performance testing.



DEFINITIONS:

Diamond Accuracy	<i>Diamond</i> test stones correctly classified as <i>Diamond</i> .
Synthetic Diamond Accuracy	<i>Synthetic Diamond</i> test stones correctly classified as <i>Synthetic Diamond</i> .
Diamond Simulant Accuracy	<i>Diamond Simulant</i> test stones correctly classified as <i>Diamond Simulant</i> .
Diamond Referral Rate	<i>Diamond</i> test stones classified as <i>Referral</i> .
Synthetic Diamond Referral Rate	<i>Synthetic diamond</i> test stones classified as <i>Referral</i>
Simulant Referral Rate	<i>Diamond simulant</i> test stones classified as <i>Referral</i>
Diamond False Positive Rate	Synthetic diamonds /diamond simulants test stones incorrectly classified as <i>Diamond</i> .
Synthetic Diamond False Positive Rate	Diamonds/ Diamond simulants test stones incorrectly classified as Synthetic Diamond.
Diamond Simulant False Positive Rate	Diamonds /Synthetic Diamonds test stones incorrectly classified as Diamond Simulants.
Diamond False Negative Rate	Diamonds test stones incorrectly classified as Synthetic Diamonds or Diamond simulants.
Synthetic Diamond False Negative Rate	Synthetic Diamonds test stones incorrectly classified as Diamonds or Diamond simulants
Diamond Simulant False Negative Rate	Diamond Simulant test stones incorrectly classified as Diamonds or Synthetic Diamonds
Testing Speed	The average speed at which the diamond verification instrument evaluates the stones in the PRIMARY loose sample set, including set-up time (if any)
Operating Speed	For auto-loading diamond verification instruments only, the average speed at which stones are evaluated once the instrument achieves a steady-state. Does not include set-up time.

TEST STONE SETS USED FOR EVALUATION

Loose, Polished Stone Test Sets	Diamond	Synthetic Diamond	Diamond Simulant
Primary Sample Set (>2.0 mm, D-J color)	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Supplementary Smalls Sample Set (1.0-2.0 mm, D-J color)	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Supplementary Ultra Smalls Sample Set (0.5- 1.0mm)	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Mounted, Polished Stone Test Sets	Diamond	Synthetic Diamond	Diamond Simulant
Primary Sample Set (>2.0 mm, D-J color)	<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
Supplementary Smalls Sample Set (1.0-2.0 mm, D-J color)	<input type="checkbox"/>	<input type="checkbox"/>	

Notes: In Primary loose sample set, stones greater than 3.8 mm diameter were excluded from testing due to upper size limit for this instrument. This instrument cannot test mounted jewelry.



CLEANING PROCEDURE OF STONES PRIOR TO TESTING

Test stones sets are cleaned in an ultrasonic bath of isopropanol for 2 minutes and dried prior to testing to reduce grease and electrostatic charge, as per Section 8 of ASSURE Standard.

LABORATORY CONDITIONS AT TIME OF ASSESSMENT

Condition	Requirement	Actual
Temperature (°C)	18 to 25°C	23 °C
Humidity (%)	50 to 65%	56 %

RESULTS OF INSTRUMENT PERFORMANCE ASSESSMENT – LOOSE STONES

Performance Metric	Primary ^[1]	Uncertainty ^[2]	Smalls	Uncertainty ^[2]	Ultra-Smalls ^[4]
Diamond accuracy (%)	98.4	0.3	99.1	0.2	97.4
Synthetic diamond accuracy (%)	0.0 ^[3]	0.0	0.0 ^[3]	0.0	0.0 ^[3]
Diamond simulant accuracy (%)	100.0	0.0	100.0	0.0	100.0
Diamond referral rate (%)	1.6	0.3	0.9	0.2	2.6
Synthetic diamond referral rate (%)	100.0 ^[3]	0.0	100.0 ^[3]	0.0	100.0 ^[3]
Diamond simulant referral rate (%)	0.0	0.0	0.0	0.0	0.0
Diamond false positive rate (%)	0.0	0.0	0.0	0.0	0.0
Synthetic diamond false positive rate (%)	0.0	0.0	0.0	0.0	0.0
Diamond simulant false positive rate (%)	0.0	0.0	0.0	0.0	0.0
Diamond false negative rate (%)	0.0	0.0	0.0	0.0	0.0
Synthetic diamond false negative rate (%)	0.0	0.0	0.0	0.0	0.0
Diamond simulant false negative rate (%)	0.0	0.0	0.0	0.0	0.0

- Notes: ^[1] Primary stone set deviates from the standard as a reduced number of stones were analyzed. The Primary sample has a total of 500 mixed stones of which 470 stones were tested due to removal of stones greater than 3.8 mm diameter.
- ^[2] Uncertainty is expressed as absolute +/- range and reflects the consistency of the instrument’s classification of stones for each of the three trials performed with the ASSURE sample.
- ^[3] All Synthetic Diamonds reported as referral for this instrument
- ^[4] Ultra- smalls sample set only tested once



Date:	12 January 2026	Testing ID:	2026-01
--------------	-----------------	--------------------	---------

INSTRUMENT TESTING SPEED ASSESSMENT

Testing Speed approximates the usage turnaround time that could be expected by a novice user of the diamond verification instrument and is determined by the time required to evaluate the performance of the diamond verification instrument on the Primary Loose stone test set:

- Testing Speed accounts for the time directly associated with stone assessment including loading stones, programming any applicable instrument measurement parameters, analyzing the stones, and segregating the analyzed stones into respective instrument classified groups.
- Testing Speed does not include the time to initially warm-up the diamond verification instrument (if applicable) nor the time to separate diamonds from synthetic diamonds for each of the instrument classified groups of analyzed stones.
- Testing Speed does not include time associated with interruptions to the testing process.

Diamond verification instruments that continuously load and analyze stones (i.e., autoloading diamond verification instruments) shall also be assessed for a steady-state Instrument Operating Speed.

Testing speed, and instrument operating speed if applicable, are measured in triplicate. The mean value is reported in the Speed Test Results table below. The Uncertainty reflects the absolute +/- range of the results measured over the three trials.

SPEED TEST RESULTS (PRIMARY LOOSE SAMPLE)

Category	Stones per hour	Uncertainty
Testing Speed (all devices)	725	18
Operating Speed (auto-loading devices)	862	12

Notes: none

ADDITIONAL FINDINGS

***** End of Report *****